



Technical Data Sheet

March 2008
Product Code: 1320001

Axter Limited

West Road Ransomes Europark
Ipswich Suffolk IP3 9SX
Tel (01473) 724056 Fax (01473) 723263
Email info@axterltd.co.uk

www.axter.co.uk

NB: The manufacturer reserves the right without prior notice to modify the composition of his products. Characteristics provided in this publication derive from data obtained under controlled test conditions. AXTER Limited makes no warranties, express or implied as to the properties and performance under any variations from such conditions in actual construction.

THERMECRAN

INTRODUCTION	THERMECRAN is high strength, glass-fibre reinforced oxidised bitumen perforated membrane with a polyester film under surface								
USE	As a layer to provide partial adherence in torch-on single or multi-layer waterproofing systems such as HYRANGER TS. As a diffusion layer under a torched on vapour control layer.								
PACKAGING	20 m ² rolls (20m x 1m) with a nominal weight of 32 kg.								
STORAGE	Rolls to be stored upright, without stacking and under cover.								
COMPOSITION	<table><tr><td>Perforated high strength glass fibre reinforcement</td><td>50 gm/m²</td></tr><tr><td>Oxidised bitumen</td><td>1200 gm/m²</td></tr><tr><td>Surface finish: sand</td><td>300 gm/m²</td></tr><tr><td>Under surface finish: polyester film</td><td>10 gm/m²</td></tr></table>	Perforated high strength glass fibre reinforcement	50 gm/m ²	Oxidised bitumen	1200 gm/m ²	Surface finish: sand	300 gm/m ²	Under surface finish: polyester film	10 gm/m ²
Perforated high strength glass fibre reinforcement	50 gm/m ²								
Oxidised bitumen	1200 gm/m ²								
Surface finish: sand	300 gm/m ²								
Under surface finish: polyester film	10 gm/m ²								
CHARACTERISTICS <i>Binder</i>	<table><tr><td>Melting point (ring & ball) (BS EN 1427)</td><td>100 °C</td></tr><tr><td>Penetration at 25° C (BS EN 1426)</td><td>40 1/10⁹mm</td></tr></table>	Melting point (ring & ball) (BS EN 1427)	100 °C	Penetration at 25° C (BS EN 1426)	40 1/10 ⁹ mm				
Melting point (ring & ball) (BS EN 1427)	100 °C								
Penetration at 25° C (BS EN 1426)	40 1/10 ⁹ mm								